



# INSTANT ADHESIVE BLACK SEMI-GEL • RUBBER TOUGHENED

PART NO. **CA500RT**

## DESCRIPTION

CA500RT is a black, medium viscosity, rubber-toughened ethyl instant adhesive. It provides superior shock and thermal resistance when bonding rubbers, metals, and plastics in harsh environments, and displays excellent strength and flexibility on a variety of substrates.

## PHYSICAL PROPERTIES

Technology / Base	Modified Ethyl
Type of Product	Cyanoacrylate
Components	One Component
Curing	Humidity
Appearance / Color	Black
Consistency	Semi-Gel

## TECHNICAL DATA

Property	Value	Method/Condition
<b>Rheology</b>		
Viscosity	500 +/- 100 cPs	Brookfield SC4-21, @ 25°C
<b>Density</b>		
Specific Gravity	1.06	N/A
<b>Uncured Materials Characteristics</b>		
Flash Point	80°C (176°F)	N/A
Set Time		
Steel (sec)	<60	N/A
ABS (sec)	<50	N/A
EPDM (sec)	<40	N/A
Shelf Life	12mo	N/A
<b>Cured Materials Characteristics</b>		
Full Cure Time	24 hours	N/A
Cure Appearance	Black	N/A
Service Temperature	-55 to 140°C	N/A
<b>Cured Mechanical Properties</b>		
See Graphs and Table		



## INSTRUCTIONS

Surfaces to be bonded should be clean and dry. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film layer after compression. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute and maximum strength is attained in 24 hours. Wipe off excess adhesive from the top of the container and recap. Products, if left uncapped, may deteriorate by contamination from moisture in the air. Because products cure by polymerization, whitening may appear on the surface of the container or the bonded materials. This will not affect adhesive performance.

## CURING PERFORMANCE

Ambient surface moisture initiates the curing process. Handling strength is reached in a short time, and will vary based on environmental conditions, bond line gap, and other factors. Product will continue to cure for at least 24 hours before full strength and solvent resistance is developed.

## STORAGE

Containers should be stored in a cool, dry, dark area. Storage temperature 15.5°C - 25°C (60°F - 77°F), without exposure to direct light or heat. Do not refrigerate.

## SPECIFICATIONS AND APPROVALS


Mil-A-46050C, Type II Class 3,  
CID A-A-3097, Type II Class 3

## SAFETY & DISPOSAL

For safe handling information and disposal instructions on this product, consult the Safety Data Sheet (SDS).




## HOT STRENGTH %RT Strength, Tested at Temperature



## SOLVENT RESISTANCE

Solvent	Resistance
Alcohol	Excellent
Ester (aromatic)	Excellent
Ketone (aromatic)	Poor
Aliphatic hydrocarbon (alkanes)	Good
Aromatic hydrocarbons	Good
Halogenated hydrocarbons	Poor
Weak aqueous acid	Excellent (Poor if concentrated)
Weak aqueous base	Excellent (Poor if concentrated)

## HEATING AGING Aged at Temperature Indicated & Tested at 22°C




## PERFORMANCE OF CURED ADHESIVE


Substrate	N/mm <sup>2</sup>	PSI
Steel	13.8 to 24.1	2000 to 3500
Rubber*	4.9 to 15.2	710 to 2200
AL	18.0 to 21.5	2610 to 3115
PC**	17.8 to 26.0	2585 to 3770
PVC**	11.4 to 21.4	1655 to 3110
ABS**	15.5 to 17.2	2250 to 2500

\*Rubber figures given are typical. Your results may vary by specific rubber type.  
 \*\*Tested to ASTM 4501      \*\*\*n/r = not recommended

## TIME UNTIL FULL CURE %RT Strength



## PERFORMANCE RANGE BY SUBSTRATE (N/mm<sup>2</sup>)



## DISCLAIMER

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is user's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the user's intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Unless otherwise noted, trademarks are property of H.B. Fuller Company or one of its affiliated entities. Gorilla and GorillaPro are registered trademarks of The Gorilla Glue Company.  
 © H.B. Fuller Company, 2022.

TDS - Instant Adhesive - CA500RT - Updated 11-10-2021



**GorillaPro.com**

9001 W. Fey Dr. · Frankfort, IL 60423 · +1-888-676-7763  
 SUPPORT: 1-888-MRO-PROF, gorillapro@hbfuller.com



**H.B. Fuller**